



## TEST REPORT ON WEATHERING RESISTANCE

Client	Smith Line Reinforced Composites FZ-LLC PO Box:6523 Ras Al Khaimah, UAE		
Sample Description	GRP	Lab Report No.	WLRP20-3725/9
Source	Smith Line Reinforced Composites FZ-LLC	Sample No.	WSP20-3725
Test Method	ASTM G154-16	Date Received	29/12/2020
Test Procedure	ASTM D151-10	Cast Date	Not Applicable
Evaluation Test Method	ASTM D714-02	Date Tested	17/01/2021-07/02/2021
Devise Type	Weathering Apparatus	Date Reported	09/02/2021
Light Source	UVA-340	Room Temperature	23°C
Cycle	8 hours UV at 60°C and 4 hours condensation at 50°C	Relative Humidity	50%
Exposure Duration	500 Hours	Sample brought in by	Client
Client Reference	N.G	Tested By	SU

### Test Results

Test	Observation
Artificial Weathering (500 Hrs)	No cracking , No chalking, No flaking, No wrinkling No blistering or any other type of failure observed.

Remarks: None.

Signed for and on behalf of Wimpey Laboratories

S.Sarath Kumar  
Senior Technician

Test results relate only to the samples tested.

This report shall not be reproduced except in full, without the written approval of the laboratory.

-End of Text-








**Annex A**

**TEST PHOTOS**



**Before Test**



**After Test**

**Report Number: WLRP20-3725/9**

**Sample Number: WSP20-3725**

